

SARAN™ 560 Vapor Retarder Tape

SARAN™ 560 Vapor Retarder Tape is composed of durable, flexible polyvinylidene chloride (PVDC) coated with a pressure sensitive acrylic adhesive designed for effective and long-lasting adhesion to a variety of substrates. Designed specifically for high vapor drive applications, SARAN 560 Tape conforms easily to fittings, elbows and joints, creating a tight, water-resistant seal and protecting these vulnerable areas from moisture intrusion and energy loss. A permeance rating of 0.01 perms meets or exceeds the strictest industry requirements for vapor retarders in cold service.

Applications

SARAN™ 560 Vapor Retarder Tape is used to wrap elbows and fittings in many high-moisture environments over a wide temperature range. The high performance tape is also used to seal butt joints and seams in the vapor retarder system.

Typical applications for SARAN 560 Tape include:

- Food and beverage facilities
- Chilled water piping and HVAC systems
- Transport pipelines
- Chemical condensation tanks
- Cold storage systems
- Refrigerated transport
- Pharmaceutical plants
- Petrochemical plants
- Cryogenic systems, including liquefied natural gas (LNG)

ITW can provide general guidelines and recommendations on many typical applications for SARAN 520 Vapor Retarder Tape. Call 1-800-231-1024 or contact your local ITW representative for details.

SIZE

SARAN™ 560 Vapor Retarder Tape is sold in rolls.

- Width: 2" (5 cm)
 3" (7.5 cm)
 Length: 50 yards (46 m)

PHYSICAL PROPERTIES

SARAN™ 560 Vapor Retarder Tape exhibits the properties and characteristics indicated in Table 1 when tested as represented.

Consultation with local code officials or design engineers/specifiers is recommended before application.

TABLE 1

Physical Properties ⁽¹⁾ of SARAN™ 560 Vapor Retarder Tape	
Property and Test Method	Value
Permeance ⁽²⁾ , ASTM E96, perm	0.01
Adhesion to Steel, ASTM D3330, oz/in	
Initial	30
After 3 days @72°F	50
Adhesion to SARAN™ Film, ASTM D3330, oz/in	
Initial	55
After 3 days @ 72°F	60
Backing Thickness, ASTM D374, mils, avg	6
Adhesive Thickness, ASTM D3652, mils, avg	1.5
Tensile Strength, ASTM D3759, lb/in ²	55
Elongation at Break, ASTM D3759, %	145
Surface Burning Characteristics ⁽³⁾ , ASTM E84	
Flame Spread	5
Smoke Developed	30
Service Temperature Limits ⁽⁴⁾ , °F (°C)	-40 to 250 (-40 to 121)
Color	White

- (1) Data shown are typical values obtained from representative samples. This data may be used as a guide for design purposes, but should not be construed as specifications.
- (2) 1 perm = 1 gr/hr/ft²/in•Hg @ 73°F, 50% R.H.
- (3) This numerical flame spread data is not intended to reflect hazards presented by this or any other material under actual fire conditions.
- (4) Service temperature limits is defined as the temperature to which the jacket or coating may be subjected when applied over insulation. It does not refer to the operating temperature of the equipment, vessel or pipe. (Source: National Insulation Association)

For maximum tape flexibility during installation, it is recommended that SARAN Tape products be installed at ambient temperatures above 24°F (-4°C).

SARAN™ 560 Vapor Retarder Tape

*Trademark of The Dow Chemical Company

Installation

SARAN™ 560 Vapor Retarder Tape can be installed at ambient temperatures as low as 0°F (-18°C). For maximum tape flexibility during installation, it is recommended that SARAN Tape products be installed at ambient temperatures above 24°F (-4°C). SARAN 560 Vapor Retarder Tape has service temperature limits of -40°F to 250°F (-40°C to 121°C).

The temperature during short term storage or shipping of cases cannot exceed 110°F (43°C).

Recommended shelf life is 12 months when stored at 60°F to 80°F (16°C to 32°C) and 50% R.H.

Because of the critical technical design aspects of many of the applications of SARAN 560 Vapor Retarder Tape, ITW recommends that qualified designers specify the total system. Detailed installation guidelines for SARAN Vapor Retarder Film and Tape products are available at www.itwinsulation.com.

Availability

SARAN™ 560 Vapor Retarder Tape is distributed through ITW's extensive Authorized Fabricator Network. For more information, call: 1-800-231-1024

Technical Services

ITW can provide technical information to help address questions when using SARAN™ 560 Vapor Retarder Tape. Technical personnel are available at: 1-800-231-1024

- **For Technical Information: 1-800-231-1024**
- **For Sales Information: 1-800-231-1024**
- ITW Insulation Systems
- 1370 East 40th Street, Building 7, Suite 1, Houston, TX 77022-4104
- www.itwinsulation.com

NOTICE: No freedom from any patent owned by ITW or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. ITW Insulation Systems assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

COMBUSTIBLE: Protect from high heat sources. Local building codes may require a protective or thermal barrier. For more information, call ITW at 1-800-231-1024 or contact your local building inspector.

Building and/or construction practices unrelated to insulation could greatly affect moisture and the potential for mold formation. No material supplier including ITW can give assurance that mold will not develop in any specific system.

***ITW* Insulation Systems**

*Trademark of ITW Insulation Systems

Form No. ST56001-1108